

## Technical Data Sheet

### 2057 Double Sided Polypropylene (with a glassine paper liner)

<u>Technical Details</u>	<u>Typical Value</u>	<u>Units</u>
Thickness, adhesive & carrier	0.090	mm
Release liner thickness	0.068	mm
180 degree peel adhesion		
Open side	1000	N/m
Closed side	1000	N/m
Polyester loop tack:		
Open side	1000	N/m
Closed side	1000	N/m
Liner release	10 max	N/m
Tensile strength	2200	N/m
Elongation at break	75	%
Service temperature	-15 to 75	Deg.C
Recommended Application Temperature	+5 to +25	Deg.C
Shear adhesion, 1kg @ 23 deg.c	Greater than 100	Hours
Shelf life	12	Months

Test Methods: BS7116

**Note:**

The above information is given in good faith and for guidance only.

All data is based upon average values. The purchaser shall be responsible for determining the suitability of this product for their purposes.